

AMCC 10





ISOMETRIC VIEW

PHYSICAL SPECIFICATIONS	CORE BUILD (a)	WINDOW WIDTH (b)	WINDOW LENGTH (c)	CORE HEIGHT (d)	CORE WIDTH (e)	CORE LENGTH (f)	WEIGHT OF CORE # (g)
<u>(mm)</u>	11.0	13.0	40.0	20.0	35.0	62.0	198
TOLERANCES (mm)	±0.8	MIN.	MIN.	±0.5	+1.0 / -0.5	+2.0 / -0.0	NOM.

WEIGHT INCLUDES 2% (NOM.) EPOXYWEIGHT.

CALCULATED	STACK FACTOR	MEAN MAGNETIC PATH LENGTH (lm)	NET CROSS SECTIONAL AREA (Ac)	WINDOW AREA (Wa)	AREA PRODUCT (Ap)
SPECS	% cm		cm ²	cm ²	cm ⁴
	82%	15.0	1.8	5.2	9.4
TOLERANCES	±2%	NOM.	NOM.	NOM.	NOM.

TEST SPECIFICATIONS	CORE LOSS @ 16kHz, 0.037T
	≤ 1.38 W / Kg
TOLERANCES	Max.

* All measurements are done at Room Temperature (22°C to 28°C).

IMENSIONS

* Continuous Operating Temperature: 150°C (Max.)

- 1. Customer to mark the dimensions/characteristics that are critical to fit/form and function on the drawing.
- 2. Number of components to be submitted for pilot production lot=
- 3. Unless otherwise specified, standard packaging used by hitachi metglas will be provided.
- All production records and data pertaining to this product will be retained for a period of 1 year from the date of shipment.
 For Product Safety communication refer EG/FM/0039

- a). Bare core, kept in open, is rust prone.
- b). Core with minor rust can be used after cleaning with suitable rust preventive chemical.
- c). Core to be shelf stored in proper packaging like VCI (Volatile Corrosion Inhibitor) paper cover. d). Core recommended to be used in application after suitable varnishing / coating / potting / covering etc.

SIGNATURE: DATE: NAME: COMPANY NAME:

DISCLAIMER: The manufacturer ensures outer dimensions & weight of each individual core conforms to specifications. However, core profile & inner window dimensions are indicative & minimum

CUSTOMER APPROVAL

This drawing, the property of Hitachi Metals India Pvt. Ltd, is furnished subject to return on demand and condition that information and technology embodied herein shall not be disclosed or used and the drawing shall not be reproduced or copied in whole or in part except as previously authorized in writing. Any person who may receive or observe this design will be held strictly liable for any violation whether willful or negligent.

TOLERANCES UNLESS OTHERWISE SPECIFIED	NO.	REVISION	BY	APPR.	DATE	DIMENSI
	03	ADDED NOTE#3. (AS PER PCN002).	SA	RK	26/07/04	SCALE
		PRODUCT & DRAWING FORMAT REVISED. (AS PER PCN004)	RG	RK	25/09/06	PROJEC1
		PRODUCT TOLERANCE & DRAWING FORMAT REVISED.(REFER PCN005)	AS	RG	16/05/08	€'
	06	PRODUCT DRAWING FORMAT REVISED.	RNS	RG	29/05/15	, , , , , , , , , , , , , , , , , , ,
	07	PRODUCT DRAWING FORMAT REVISED.	MR	RG	27/11/17] `

n dimer	nsions are	e ensured.									
nm	DESCRIPTION PRODUCT DRAWING - AMCC10						OF ET	DRAWING NO.		RE'	
.T.S		111000	OI DILAWIN	a - Allioo io		Oil		10.		-	
.1.3	PRIME I	RAW MATER									
		1 OF 1		AMCC10		07					
		DDAMAI	DATE	OUEOUED.	D.4.T	_	400	DO1/ED			
			DATE			_				т	

PROJECTION 🕀 Materials Mag!c Hitachi Metals 07/12/01 07/12/01 RH,RM,ST 07/19/01

FM NO.: EG/FM/0011. Rev. No.: 8. Date: 26.10.2017 REFERENCE PROJECT DRG. NO:-