

## AMCC500





PHYSICAL SPECIFICATIONS	CORE BUILD (a)	WINDOW WIDTH (b)	WINDOW LENGTH (c)	CORE HEIGHT (d)	CORE WIDTH (e)	CORE LENGTH (f)	WEIGHT OF CORE # (g)
( <u>mm)</u>	25.0	40.0	85.0	55.0	90.0	135.0	2,890
TOLERANCES (mm)	±1.0	MIN.	MIN.	±1.0	+1.0 / -0.5	+4.0 / -0.0	NOM.

# WEIGHT INCLUDES 2% (NOM.) EPOXY WEIGHT.

CALCULATED	STACK FACTOR	MEAN MAGNETIC PATH LENGTH (lm)	NET CROSS SECTIONAL AREA (Ac)	WINDOW AREA (Wa)	AREA PRODUCT (Ap)	
SPECS	%	cm	cm <sup>2</sup>	cm <sup>2</sup>	cm <sup>4</sup>	
	82%	35.0	11.3	34.0	383.4	
TOLERANCES	±2%	NOM.	NOM.	NOM.	NOM.	

TEST SPECIFICATIONS	CORE LOSS @ 16kHz, 0.037T
	≤ 1.38 W / Kg
TOLERANCES	Max.

- \* All measurements are done at Room Temperature (22°C to 28°C).
- \* Continuous Operating Temperature: 150°C (Max.)

- 1. Customer to mark the dimensions/characteristics that are critical to fit/form and function on the drawing.
- 2. Number of components to be submitted for pilot production lot=
- 3. Unless otherwise specified, standard packaging used by hitachi metglas will be provided.
- All production records and data pertaining to this product will be retained for a period of 1 year from the date of shipment.
   For Product Safety communication refer EG/FM/0039

TOLERANCES UNLESS OTHERWISE SPECIFI

- a). Bare core, kept in open, is rust prone.
- b). Core with minor rust can be used after cleaning with suitable rust preventive chemical.
- c). Core to be shelf stored in proper packaging like VCI (Volatile Corrosion Inhibitor) paper cover. d). Core recommended to be used in application after suitable varnishing / coating / potting / covering etc.

SIGNATURE: DATE: NAME: COMPANY NAME:

**CUSTOMER APPROVAL** 

DISCLAIMER: The manufacturer ensures outer dimensions & weight of each individual core conforms to specifications. However, core profile & inner window dimensions are indicative & minimum of the conformation of the conformatio

This drawing, the property of Hitachi Metals India Pvt. Ltd, is furnished subject to return on demand and condition that information and technology embodied herein shall not be disclosed or used and the drawing shall not be reproduced or copied in whole or in part except as previously authorized in writing. Any person who may receive or observe this design will be held strictly liable for any violation whether willful

compinis to specifications. However, core profile a filler window difficulties are indicative a millimum to									
IED	NO.	REVISION	ву	APPR.	DATE	DIMENSIONS	mm		
	03	ADDED NOTE#3. (AS PER PCN002).	SA	RK	26/07/04	SCALE	N.T.		
	04	PRODUCT & DRAWING FORMAT REVISED. (AS PER PCN004)	RG	RK	25/09/06	PROJECTION	\$		
	05	PRODUCT TOLERANCE & DRAWING FORMAT REVISED.(REFER PCN005)	AS	RG	16/05/08		aterial		
	06	PRODUCT DRAWING FORMAT REVISED.	RNS	RG	29/05/15	ÿ•• ∰ Hita	achi		
	07	PRODUCT DRAWING FORMAT REVISED.	MR	RG	27/11/17	<b>V</b> 1			

ľ	ıum dimer	nsions are	e ensured.									
	mm	DESCRIPTION PRODUCT DRAWING - AMCC500					NO. OF SHEET		DRAWING NO.		REV.	
	N.T.S			O. D. D. W.	. A.III 0000	•	0111		1		140.	
N.1.3	PRIME RAW MATERIAL											
	<b>\Phi</b>		METGLAS <sup>®</sup> ALLOY 2605SA1				1 OF 1		AMCC500		07	

Materials Mag!c DRAWN DATE CHECKED DATE APPROVED Hitachi Metals 07/12/01 07/12/01 RH,RM,ST 07/19/01

FM NO.: EG/FM/0011, Rev. No.: 8, Date: 26,10,2017

REFERENCE PROJECT DRG. NO:-

REV.:-